

جرانول خشن كومبيت

الوصف والإستخدام

دهان زخرفي عالي الجودة بأساس الفينيل كوبوليمر للإستخدام الخارجي مصنع بالكوارتز و أجود أنواع المواد الرابطة و المخضبات التي لاتتأثر بالعوامل الجوية.

المميزات:

- مناسب للظروف الجوية القاسية وفى المناطق الساحلية المعرضة للأملح والرطوبة
- يستخدم على المحارة مباشرة دون الحاجة لمعجون أو برايمر أو سيلر أو أي أوجه تحضيرية
- ثبات عالي للألوان يدوم لسنوات.
- أقتصادي من حيث الجودة العالية ومعدلات الفرد مقارنة بمواد البيض الأخرى

خصائص الدهان

المظهر النهائي	مطفي - خشن	زمن الجفاف (٢٥°س)	٢٤ ساعة
الكثافة النوعية	١,٧ ± ٠,٢	جفاف سطحي	٧ يوم
المواد الصلبة بالحجم	٧٠% ± ٥	جفاف لإعادة الطلاء	٢ مم
مادة التخفيف	ماء الصنبور	جفاف نهائي	
		سمك الفيلم الجاف المقترح	

تعليمات التطبيق

يجب أن يكون السطح خاليا تماما من الزيوت و الدهون و أي شوائب أخرى.

يطبق جرانول باستخدام الفرشاة أو الرول أو الرش أو الفرطاسة.

يجب تقليب المنتج جيدا قبل الاستخدام.

معدل التغطية

من ١ إلى ١,٥ متر مربع للكيلو للوجه الواحد باستخدام الرولة و من ٢ إلى ٢,٥ متر مربع للكيلو للوجه الواحد باستخدام البروة و ٢,٥ - ٢,٥ متر مربع للكيلو للوجه الواحد باستخدام الفرطاسة مع مراعاة نسب التهدير (معدل الفرد يختلف باختلاف طبيعة السطح وطريقة تجهيزه والأدوات المستخدمة وفاعليتها).

نظام الدهان المقترح

يرطب السطح بالماء ثم يدهن مباشرة على الحوائط و يمكن تطبيق الجرانول الخشن الكومبيت بطرق مختلفة :

الاولى : يتم تطبيقه باستخدام البروة ثم يتبع ذلك تمشيط السطح باستخدام الفرطاسة للحصول على الشكل الزخرفي المطلوب.

الثانية : يتم تطبيقه باستخدام البروة ثم يليه وجه نهائي مخفف ٥٠% بالرولة للحصول على سماكة من ١,٥ إلى ٢ مم.

الثالثة : يتم تطبيق وجه أول مخفف ١٠-٢٠% ثم يطبق وجه اخر بالرولة مخفف بحد أقصى ٣ - ٥% حسب ارتفاع الحبة المطلوبة.

الرابعة: يتم التطبيق بواسطة ماكينة الرش ويكون الوجه الاول مرشوش أفقيا والثاني مرشوش راسيا.

التخزين والصلاحيه

١٢ شهر في العبوة الأصلية المغلقة شرط سلامة العبوة وجودة التخزين.

يراعى التخزين في مكان جيد التهوية بعيداً عن أشعة الشمس المباشرة أو البرودة الشديدة.

الأمان والصحة والبيئة

يجب مراعاة التعليمات المدونة على العبوة. يراعى الإستخدام في مكان جيد التهوية وإرتداء الملابس الواقية المناسبة.

في حالة ملامسة الجلد يجب إزالة المادة بالماء والصابون. في حالة ملامسة العين يجب غسلها بكثير من الماء وإستشارة طبيب فوراً.

لا يجب التخلص من الكميات الزائدة بإلقائها في مجاري الماء.

في جميع الأحوال يجب مراعاة القوانين البيئية والمهنية المحلية.

المعلومات المبينة في هذه المواصفة قائمة على إختبارات معملية وخبرات عملية. نظراً لإستخدام المنتج في ظروف خارجة عن تحكم الشركة فإننا لا نضمن إلا جودة المنتج نفسه. للشركة الحق في تغيير أي من البيانات بدون سابق إعلام.

للمزيد من المعلومات يرجى الإتصال بالإدارة الفنية

الإدارة العامة: ٢٧ طلعت حرب الإسكندرية

ت: ٣٦/٤٨٦٨٩٣٥ (٣) ف: ٤٨٦٨٩٢٥ (٣)

المصانع والإدارة الفنية: ك ٢٥ طريق إسكندرية القاهرة الصحراوي

ت: ٢/٤٧٠١١٠ (٣) ف: ٤٧٠١١٤١ (٣)



GRANOL GS COMPETE

Product Description	<p>GRANOL GS COMPETE is a top quality texture coating that combines maximum protection with decorative textured appearance.</p> <p>Features:</p> <ul style="list-style-type: none">- Suitable for maximum weather condition protection.- Excellent color stability- Maximum abrasion and scuff resistance																				
Technical Properties	<table border="1"><tr><td>Finish</td><td>Flat / Coarse</td><td>Drying Time @25°C</td><td></td></tr><tr><td>Specific Gravity</td><td>1.7 ± 0.05</td><td>Touch Dry</td><td>24 Hours</td></tr><tr><td>Solids Volume</td><td>70% ± 2</td><td>Recoat</td><td>—</td></tr><tr><td>Thinner</td><td>Water</td><td>Complete</td><td>7 days</td></tr><tr><td></td><td></td><td>Recommended DFT</td><td>2 mm</td></tr></table>	Finish	Flat / Coarse	Drying Time @25°C		Specific Gravity	1.7 ± 0.05	Touch Dry	24 Hours	Solids Volume	70% ± 2	Recoat	—	Thinner	Water	Complete	7 days			Recommended DFT	2 mm
Finish	Flat / Coarse	Drying Time @25°C																			
Specific Gravity	1.7 ± 0.05	Touch Dry	24 Hours																		
Solids Volume	70% ± 2	Recoat	—																		
Thinner	Water	Complete	7 days																		
		Recommended DFT	2 mm																		
Processing Information	<p>Substrate must be free of oil, algae, dirt and all other contaminants. Product Should be well stirred before usage. Could be applied either by brush or roller.</p>																				
Theoretical Coverage	<p>1 - 1.5 Kilogram/Sqm/Coat if applied by roller & 2 - 2.25 Kilogram/Sqm/Coat if applied by trowel. (The Actual coverage depends on substrate nature and preparation, method of application, condition of tools, etc...)</p>																				
Recommended Application System	<p>GRANOL GS COMPETE could be applied by several ways:</p> <ul style="list-style-type: none">- Apply by metal trowel then lightly scrub the surface using plastic trowel for the desired texture.- Apply one coat by metal trowel then a second coat diluted 50% by roller to achieve a thickness of 1.5 - 2 mm.- Apply one coat diluted 10-20% then a second coat diluted 3-5% by roller according to the desired texture.																				
Storage	<p>One year from date of production in original sealed package. Product must be stored in well ventilated area away from direct sunlight, heat sources or freezing temperatures.</p>																				
Health, Safety & Environment	<p>Please observe the precautionary notice displayed on the container. Use under well ventilated conditions wearing suitable protective clothes. In case of skin contact wash with water and soap. In case of eye contact, wash thoroughly with plenty of water and seek medical attention. Excess Paint should never be spilled in water sewers. At all time local environmental laws and regulations should be maintained.</p>																				

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part. As application conditions are out of our control we can not guarantee but the quality of the product itself. PROTALL reserves the right to make any changes without prior notice.

For more Information please contact Technical Support

Headquarters: 27 Talaat Harb St. Alexandria
Tel.: +203 4868935/36 Fax.: +203 4868925

Factories & Technical Support: Km 25-26 Alex-Cairo road
Tel.: +203 4701110/20 Fax.: +203 4701141