

بروتال



مواصفة فنية متخصصة

51225-2018-V1

بونجي

الوصف والإستخدام

دهان مائي مطفرء عالي الجودة ناصع البياض للتشطيبات الداخلية.
المميزات:
- قدرة تغطية ممتازة
- إقتصادي وسهل الإستخدام
- قابلية عالية للتخفيف

خصائص الدهان

المظهر النهائي	مط / ناعم	زمن الجفاف (س ^{٢٥})
الكثافة النوعية	1,6 ± ٠,٥	جفاف سطحي
المواد الصلبة بالحجم	٤٢% ± ٢	جفاف لإعادة الطلاء
مادة التخفيف	ماء الصنبور	جفاف نهائي
		سمك الفيلم الجاف المقترح
		٤٠ ميكرون

تعليمات التطبيق

يجب أن يكون السطح خاليا تماما من الزيوت و الدهون و أي شوائب أخرى.
يطبق باستخدام الفرشاه أو الرولة أو الرش.
يراعى تقليب المنتج قبل الاستخدام.
يخفف بالماء بنسبة لا تتعدى عشرون بالمائة طبقاً لطريقة الإستخدام.

معدل التغطية

من ٦ إلى ٨ متر مربع للكيلو للوجه الواحد (معدل الفرد يختلف باختلاف طبيعة السطح وطريقة تجهيزه والأدوات المستخدمة وفعاليتها).

نظام الدهان المقترح

- وجه واحد ماكسي سيل ١٠٠٠
- ٢ سكينه معجون ماكسي فليكس ٧٠٠
- وجه أول بونجي مخفف بنسبة ١٥% ماء.
- ٢ وجه ثاني بونجي مخفف بنسبة ٥% ماء.

التخزين والصلاحيه

١٢ شهر في العبوة الأصلية المغلقة شرط سلامة العبوة وجودة التخزين.
يراعى التخزين في مكان جيد التهوية بعيداً عن أشعة الشمس المباشرة أو البرودة الشديدة.

الأمان والصحة والبيئة

يجب مراعاة التعليمات المدونة على العبوة. يراعى الإستخدام في مكان جيد التهوية وإرتداء الملابس الواقية المناسبة.
في حالة صعوبة التنفس يجب الخروج للهواء الطلق لمدة عشر دقائق على الأقل. في حالة ملامسة الجلد يجب إزالة المادة بالماء والصابون. في حالة ملامسة العين يجب غسلها بكثير من الماء وإستشارة طبيب فوراً.
لا يجب التخلص من الكميات الزائدة بإلقائها في مجاري الماء.
في جميع الأحوال يجب مراعاة القوانين البيئية والمهنية المحلية.

المعلومات المبينة في هذه المواصفة قائمة على إختبارات معملية وخبرات عملية. نظراً لإستخدام المنتج في ظروف خارجة عن تحكم الشركة فإننا لا نضمن إلا جودة المنتج نفسه. للشركة الحق في تغيير أي من البيانات بدون سابق إعلام.

للمزيد من المعلومات يرجى الإتصال بالإدارة الفنية

الإدارة العامة: ٢٧ طلعت حرب الإسكندرية

ت: ٣٦/٤٨٦٨٩٣٥ (٣) ف: ٤٨٦٨٩٣٥ (٣)

المصانع والإدارة الفنية: ك٥٥ طريق إسكندرية القاهرة الصحراوي

ت: ٢/٤٧٠١١٠ (٣) ف: ٤٧٠١١٤١ (٣)

www.protall.com



PONGEE

Product Description

PONGEE is an economy water based mat paint for interior use as an undercoat for walls and ceilings.

Features:

- High hiding power for dry film
- High Workability
- High Thinning capability

Technical Properties

Finish	Flat / Smooth	Drying Time @25°C		
Specific Gravity	1.6 ± 0.05		Touch Dry	1 Hours
Solids Volume	42% ± 2		Recoat	2 Hours
Thinner	Water		Complete	24 Hours
		Recommended DFT	40 microns	

Processing Information

Substrate must be free of oil, algae, dirt and all other contaminants.
Product Should be well stirred before usage
Could be applied either by brush or roller.

Theoretical Coverage

6 - 8 Sqm/Kilogram/Coat (The Actual coverage depends on substrate nature and preparation, method of application, condition of tools, etc...)

Recommended Application System

- One coat PROTALL SEALER 121
- Two coats MAXIFLEX 700
- One Coat PONGEE reduced 15% water.
- One coat PONGEE reduced 10% water.

Storage

One year from date of production in original sealed package.
Product must be stored in well ventilated area away from direct sunlight, heat sources or freezing temperatures.

Health, Safety & Environment

Please observe the precautionary notice displayed on the container. Use under well ventilated conditions wearing suitable protective clothes. In case of breathing difficulties move to open air for minimum 10 minutes. In case of skin contact wash with water and soap. In case of eye contact, wash thoroughly with plenty of water and seek medical attention.
Excess Paint should never be spilled in water sewers.
At all time local environmental laws and regulations should be maintained.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part. As application conditions are out of our control we can not guarantee but the quality of the product itself. PROTALL reserves the right to make any changes without prior notice.

For more Information please contact Technical Support

Headquarters: 27 Talaat Harb St. Alexandria
Tel.: +203 4868935/36 Fax.: +203 4868925

Factories & Technical Support: Km 25-26 Alex-Cairo road
Tel.: +203 4701110/20 Fax.: +203 4701141