



مواصفة فنية متخصصة

51450-2018-V1

برومط

الوصف والإستخدام

برومط دهان سنتيتك انامل غير لامع أو نصف لامع مصنع من أجود أنواع راتنجات الألكيد الغير قابلة للاصفرار مع إضافات و مكونات أخرى لإعطاء قوة تغطية عالية مع ثبات في اللون و مقاومة عالية للعوامل الجوية.

الدهان	ائص	خصا
--------	-----	-----

المظهر النهائي	ئىفلەن
الكثافة النوعية	۱,٥٦ ± ا,٠
المواد الصلبة بالحجم	o ± %oV
مادة التخفيف	نفط معدنی - تربنتین

۳۰ دقیقة ۶ ساعة ۲۶ ساعة

سمك الفيلم الجاف المقترح ٢٠ - ٢٥ ميكرون

زمن الحفاف (۲۵°س)

حفاف لاعادة الطلاء

جفاف سطحى

جفاف نهائی

تعليمات التطبيق

يجب أن يكون السطح خاليا تماما من الزيوت و الدهون و أي شوائب أخرى. يجب تقليب المنتج جيدا قبل الاستخدام. يطبق باستخدام الفرشاة أو الرول أو الرش

معدل التغطية

من ٩ إلى ١١ متر مربع للكيلو للوجه الواحد (معدل الفرد يختلف بإختلاف طبيعة السطح وطريقة تجهيزه والأدوات المستخدمة وفاعليتها).

نظام الدهان المقترح

. .

للأسطح الخشبية

وجه أول بروتاجلوس مخفف بنسبة ٣٠٪ سكينة + تلقيط معجون ماسترين للأخشاب وجه برومط مخفف بنسبة ١٠٪ وجه برومط مخفف بنسبة ٥٪ لنشطيبات الغاخرة يمكن إضافة وجه ثالث من برومط مخفف بنسبة ٥٪

للأسطح المطلية والسابقة التجهيز

يتم تنظيف السطح جيداً و تلقيطه بمعجون ماكسي ٧٠٠ ثم دهان طبقة من برومط مخفف بنسبة ٨٠٪، و وجه نهائي مخفف بنسبة ٥٪. للتشطيبات الفاخرة يمكن إضافة وجه ثالث من برومط مخفف بنسبة ٥٪.

للأسطح الخرسانية الجديدة

وجه سيِّار تجَّايخُ شَفَافُ لَعُلقَ مسام السطحَ و تقليل معدل الاستهلاك سكينة + تلقيط معجون بروتال ٥٠٥ أو معجون ماكسي فليكس ٧٠٠ وجه أول بروتاجلوس مخفف بنسبة ٢٠٪

وجه برومط مخفف بنسبة ١٠٪ وجه برومط مخفف بنسبة ٥٪

للأسطح المعدنية

وجه بروتال برايمر ۱۲۰ مخفف بنسبة ٥٪ وجه برومط مخفف بنسبة ١١٠ وجه برومط مخفف بنسبة ٥٪

للأسطح الجبس

وجه أول بروتاجلوس مخفف بنسبة ۳۰٪ تنعیم بمعجون بروتال ۵۰۰ وجه برومط مخفف بنسبة ۱۰٪ وجه برومط مخفف بنسبة ۲۰٪ وجه برومط مخفف بنسبة ۲۰٪

للحصول على وجه خشبي مغسول وجه أول بروتاجلوس مخفف بنسبة ٣٠٪

وجه أول بروتاجلوس مخفف بنسبة ٣٠. سكينة + تلقيط معجون ماسترين للأخشاب وجه بروتاجلوس مخفف بنسبة ٨٠. ٥ إلى ٦ وجه برومط مخفف بنسبة ٨٥. بعد تمام الجفاف تتم صنفرة السطح

االتخزين والصلاحية

الأمان والصحة والبيئة

١٢ شهر في العبوة الأصلية المغلقة شرط سلامة العبوة وجودة التخزين. يراعى التخزين في مكان جيد التهوية بعيداً عن أشعة الشمس المباشرة أو البرودة الشديدة.

يجب مراعاة التعليمات المدونة على العبوة. يراعى الإستخدام في مكان جيد التهوية وإرتداء الملابس الواقية المناسبة. في حالة صعوبة التنفس يجب الخروج للهواء الطلق لمدة عشر دقائق على الأقل. في حالة ملامسة الجلد يجب إزالة المادة بالمذيب المناسب. في حالة ملامسة العين يجب غسلها بكثير من الماء وإستشارة طبيب فوراً. لا يجب التخلص من الكميات الزائدة بإلقائها في مجاري الماء. في جميع الأحوال يجب مراعاة القوانين البيئية والمهنية المحلية.

المعلومات المبينة في هذه المواصفة قائمة على إختبارات معملية وخبرات عملية. نظراً لإستخدام المنتج في ظروف خارجة عن تحكم الشركة فإننا لا نضمن إلا جودة المنتج نفسه. للشركة الحق في تغيير أي من البيانات بدون سابق إعلام.

للمزيد من المعلومات يرجى الإتصال بالإدارة الفنية

الإدارة العامة: ۲۷ طلعت حرب الإسكندرية ت: ٣٣/٤٨٦٨٩٣٥ (٣٠) ف: ٤٦٨٨٩٢٥ (٣٠) المصانع والإدارة الفنية: ك٢٥ طريق إسكندرية القاهرة الصحراوي ت: ٢٠/١٤/١١ (٣) ف: ٤١١١١ع (٣٠)



Protall

51450-2018-V1

PROMAT

Product Description

PROMAT is a super quality synthetic paint, matt or semi-matt ,formulated with the best non-yellowing alkyd resins as with other additives to give a high hiding power, super color stability, and strong resistance to weathering effects.

Technical Properties

Finish	Flat / Smooth
Specific Gravity	1.56 ± 0.05
Solids Volume	57% ± 2
Thinner	White Spirit - Turpentine

Drying Time @25°C PROMAT 666 35 Minutes PROMAT 666/60 1 Hours

PROMAT 666/120 2 Hours Recomended DFT | 30 - 40 microns

Processing Information

Substrate must be free of oil, algae, dirt and all other contaminants. Product Should be well stirred before usage Could be applied either by brush, roller, or spray.

Theoretical Coverage

9 - 11 Sqm/Kilogram/Coat (The Actual coverage depends on substrate nature and preparation, method of application, condition of tools, etc...)

Recommended **Application System**

For wood surfaces:

One coat of **PROTAGLOSS** diluted 30% Two coats of MASTERIN 555 One coat of PROMAT diluted 10 % One coats of PROMAT diluted 5 %

For luxurious finishes apply a third coat of PROMAT diluted 5%

For painted and already-prepared surfaces:

Clean the surface and apply one coat of PROMAT diluted 10 %, and a final coat diluted 5%

For luxurious finishes apply a third coat of PROMAT diluted 5%

For washed effect:

Apply one coat of **PROTAGLOSS** diluted 30% as a primal coat Two coats of MASTERIN 555.

One coat of PROTAGLOSS diluted 10%, Apply Five to Six coats of **PROMAT** diluted 5%. After complete drying sand the surface with the appropriate sand paper.

For metal surfaces:

One coat of PRIMER 1620 diluted 5% One coat of PROMAT diluted 10 % One coat of PROMAT diluted 5 %

For Gypsum surfaces:

One coat of PROTAGLOSS diluted 30% Smooth the surface with PROTAFILL 505 One coat of **PROMAT** diluted 10 % One coats of PROMAT diluted 5 %

For new unpainted concrete surfaces:

One coat of SEALER 121diluted 30-50% with water Two coats of PROTAFILL 505 One coat of PROTAGLOSS diluted 20% One coat of PROMAT diluted 10 % One coat of PROMAT diluted 5 %,

Storage

One year from date of production in original sealed package. Product must be stored in well ventilated area away from direct sunlight, heat sources or freezing temperatures.

Health, Safety & **Enviroment**

Please observe the precautionary notice displayed on the container. Use under well ventilated conditions wearing suitable protective clothes. In case of breathing difficulties move to open air for minimum 10 minutes. In case of skin contact wash with appropriate solvent. In case of eye contact, wash thoroughly with plenty of water and seek medical attention. Excess Paint should never be spilled in water sewers.

At all time local environmental laws and regulations should be maintained.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part. As application conditions are out of our control we can not guarantee but the quality of the product itself. PROTALL reserves the right to make any changes without prior notice.

For more Information please contact Technical Support

Headquarters: 27 Talaat Harb St. Alexandria Tel.: +203 4868935/36 Fax.: +203 4868925

Factories & Technical Support: Km 25-26 Alex-Cairo road Tel.: +203 4701110/20 Fax.: +203 4701141