

## بروماكس

### الوصف والإستخدام

دهان سنتيتيك انامل شديد اللمعة، مصنع بأجود أنواع راتنجات الالكيد المقاومة للاصفرار.

المميزات:

- بياض ناصع وتغطية عالية
- مقاومة فائقة للاصفرار
- قوة إلتصاق عالية
- ثبات ممتاز للون واللمعة

مطابق للمواصفة القياسية المصرية ٧٩٣/٢٠٠٨

### خصائص الدهان

المظهر النهائي	لامع	زمن الجفاف (س <sup>٢٥</sup> )	جفاف سطحي
الكثافة النوعية	1,23 ± 0,05 (للون الأبيض)	٥ ساعة	جفاف لإعادة الطلاء
المواد الصلبة بالحجم	71 ± 3 (للون الأبيض)	٢٤ ساعة	جفاف نهائي
مادة التخفيف	نفت معدني	٣٠ - ٤٠ ميكرون	سمك الفيلم الجاف المقترح

### تعليمات التطبيق

يجب أن يكون السطح خاليا تماما من الزيوت و الدهون و أي شوائب أخرى يطبق باستخدام الفرشاه أو الرولة أو الرش. يراعى تقليب المنتج قبل الاستخدام.

### معدل التغطية

من ١٢ إلى ١٤ متر مربع للكيلو للوجه الواحد (معدل الفرد يختلف باختلاف طبيعة السطح وطريقة تجهيزه والأدوات المستخدمة وفعاليتها).

### نظام الدهان المقترح

- للأسطح الخرسانية:
- وجه أول سيلر ١٢١
  - ٢ سكينه معجون ماكسي فليكس ٧٠٠
  - وجه واحد بروتاجلوس مخفف ١٥٪
  - ٢ وجه بروماكس مخفف ١٠٪
- للأسطح الخشبية:
- ٢ سكينه معجون ماسترين ٥٥٥
  - وجه واحد بروتاجلوس مخفف ١٥٪
  - ٢ وجه بروماكس مخفف ١٠٪

### التخزين والصلاحيه

١٢ شهر في العبوة الأصلية المغلقة شرط سلامة العبوة وجودة التخزين. يراعى التخزين في مكان جيد التهوية بعيداً عن أشعة الشمس المباشرة أو البرودة الشديدة.

### الأمان والصحة والبيئة

يجب مراعاة التعليمات المدونة على العبوة. يراعى الإستخدام في مكان جيد التهوية وإرتداء الملابس الواقية المناسبة. في حالة صعوبة التنفس يجب الخروج للهواء الطلق لمدة عشر دقائق على الأقل. في حالة ملامسة الجلد يجب إزالة المادة بالمذيب المناسب. في حالة ملامسة العين يجب غسلها بكثير من الماء وإستشارة طبيب فوراً. لا يجب التخلص من الكميات الزائدة بإلقائها في مجاري الماء. في جميع الأحوال يجب مراعاة القوانين البيئية والمهنية المحلية.

المعلومات المبينة في هذه المواصفة قائمة على إختبارات معملية وخبرات عملية. نظراً لإستخدام المنتج في ظروف خارجة عن تحكم الشركة فإننا لا نضمن إلا جودة المنتج نفسه. للشركة الحق في تغيير أي من البيانات بدون سابق إعلام.

للمزيد من المعلومات يرجى الإتصال بالإدارة الفنية

الإدارة العامة: ٢٧ طلعت حرب الإسكندرية

ت: ٣٦/٤٨٦٨٩٣٥ (٣) ف: ٤٨٦٨٩٢٥ (٣)

المصانع والإدارة الفنية: ك٢٥ طريق إسكندرية القاهرة الصحراوي

ت: ٢/٤٧٠١١٠ (٣) ف: ٤٧٠١١٤١ (٣)



## PROMAX

### Product Description

Premium quality High gloss synthetic enamel paint produced with the best non yellowing alky resins and special additives.

**Features:**

- High Whiteness and hiding power
- High adhesion to surface
- Excellent anti yellowing performance
- Excellent color and gloss retention

**Conforms to Egyptian Standards 793/2008**

### Technical Properties

Finish	Glossy	Drying Time @25°C	
Specific Gravity	1.23 ± 0.05 (White)	Touch Dry	5 Hours
Solids Volume	61% ± 2 (White)	Recoat	24 Hours
Thinner	White Spirit	Recommended DFT	30-40 microns

### Processing Information

Substrate must be free of oil, algae, dirt and all other contaminants.  
Product Should be well stirred before usage  
Could be applied either by brush, roller or spray.

### Theoretical Coverage

12 - 14 Sqm/Kilogram/Coat ( The Actual coverage depends on substrate nature and preparation, method of application, condition of tools, etc...)

### Recommended Application System

**For concrete surfaces:**

- One coat PROTALL SEALER 121
- Two coats putty MAXIFLEX 700
- One coat PROTAGLOSS reduced 15%.
- Two coats PROMAX reduced 10%.

**For wood surfaces:**

- Two coats putty MASTERIN 555
- One coat PROTAGLOSS reduced 15%.
- Two coats PROMAX reduced 10%.

**For metal surfaces:**

- One coat PROTALL PRIMER 1620
- One coat PROTAGLOSS reduced 15%.
- Two coats PROMAX reduced 10%.

### Storage

One year from date of production in original sealed package.  
Product must be stored in well ventilated area away from direct sunlight, heat sources or freezing temperatures.

### Health, Safety & Environment

Please observe the precautionary notice displayed on the container. Use under well ventilated conditions wearing suitable protective clothes. In case of breathing difficulties move to open air for minimum 10 minutes. In case of skin contact wash with suitable solvent. In case of eye contact, wash thoroughly with plenty of water and seek medical attention.  
Excess Paint should never be spilled in water sewers.  
At all time local environmental laws and regulations should be maintained.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part. As application conditions are out of our control we can not guarantee but the quality of the product itself. PROTALL reserves the right to make any changes without prior notice.

### For more Information please contact Technical Support

Headquarters: 27 Talaat Harb St. Alexandria  
Tel.: +203 4868935/36 Fax.: +203 4868925

Factories & Technical Support: Km 25-26 Alex-Cairo road  
Tel.: +203 4701110/20 Fax.: +203 4701141