



COPON FILLER

PRODUCT DESCRIPTION

Two-pack epoxy putty for filling cracks, crevices and pits in surfaces like steel, wood or concrete. Possesses outstanding strength and excellent resistance to water and chemicals.

PROCESSING

Ensure that the areas to be filled are free from grease, dust, dirt or moisture. This is best achieved by use of scrapers, wire brushes and soft brushes. Grease contamination must be removed with PROTALL Thinners.

APPLICATION METHOD

Apply by filling or stopping knife, working well into the surface, and level off. To fill cavities more than 12.5 mm deep, two or more applications are advisable to ensure complete through hardening.

COLORS

Available in many color upon request.

PHYSICAL PROPERTIES

Pot Life ½ -1 ½ hours after mixing, depending upon prevailing temperature.

Hard Dry 16 Hours

Re-coat Time 16 Hours

Curing Time 3-4 days at normal temperatures (15°C-20°C)

Film thickness up to 12.5 mm thickness per application

Practical Coverage 0.30 m²/kg for 1.5 mm dry film thickness.

HEALTH & SAFETY

1. In the wet state COPON FILLER is highly inflammable
2. Adequate ventilation must be provided during use
3. Undue contact with the skin should be avoided
4. Minimum Ventilation air quantity required for 1 liter of mixed paint
 - To reach 10% of LEL 62 m³
 - To reach TLV 912 m³

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part. As application conditions are out of our control we can not guarantee but the quality of the product itself. PROTALL reserves the right to make any changes without prior notice.

For more Information please contact Technical Support

Headquarters: 27 Talaat Harb St. Alexandria
Tel.: +203 4868935/36 Fax.: +203 4868925

Factories & Technical Support: Km 25-26 Alex-Cairo road
Tel.: +203 4701110/20 Fax.: +203 4701141