

بروتال



مواصفة فنية متخصصة

51215-2023-V1

ماكسي بلاست ٣٠٠٠

دهان إقتصادي مائي بأساس الفينيل كوبوليمر لإعداد الأسطح ببطانة بلاستيكية مستحلبة بيضاء تعمل على خفض إستهلاك الطبقات التالية.

المميزات:

- قوة تغطية عالية للفيلم الجاف
- إقتصادي وسهل الإستخدام
- درجة بياض عالية
- قابلية عالية للتخفيف

الوصف والإستخدام

خصائص الدهان

المظهر النهائي	مط / ناعم	زمن الجفاف (س ^{٢٥})
الكثافة النوعية	١,٦٦ ± ٠,٥	جفاف سطحي
المواد الصلبة بالحجم	٤٢ ± ٢	جفاف لإعادة الطلاء
مادة التخفيف	ماء الصنبور	جفاف نهائي
		سمك الفيلم الجاف المقترح
		٥٠ ميكرون

تعليمات التطبيق

يجب أن يكون السطح خاليا تماما من الزيوت و الدهون و أي شوائب أخرى، كما يراعى تماسك السطح وعدم وجود تجبير أو تبدير. يطبق باستخدام الفرشاه أو الرولة. يراعى تقليب المنتج قبل الاستخدام.

معدل التغطية

من ٤ إلى ٥ متر مربع للكيلو للوجه الواحد (معدل الفرد يختلف باختلاف طبيعة السطح وطريقة تجهيزه والأدوات المستخدمة وفاعليتها).

نظام الدهان المقترح

- وجه واحد سيلر بروتال ١٢١
- ٢ - ٣ سكينه معجون فليكس ٧٠٠
- وجه أول ماكسي بلاست ٣٠٠٠ مخفف بنسبة ١٥٪ ماء.
- وجه ثاني ماكسي بلاست ٣٠٠٠ مخفف بنسبة ١٠٪ ماء.

التخزين والصلاحية

١٢ شهر في العبوة الأصلية المغلقة شرط سلامة العبوة وجودة التخزين. يراعى التخزين في مكان جيد التهوية بعيداً عن أشعة الشمس المباشرة أو البرودة الشديدة.

الأمان والصحة والبيئة

يجب مراعاة التعليمات المدونة على العبوة. يراعى الإستخدام في مكان جيد التهوية وإرتداء الملابس الواقية المناسبة. في حالة صعوبة التنفس يجب الخروج للهواء الطلق لمدة عشر دقائق على الأقل. في حالة ملامسة الجلد يجب إزالة المادة بالماء والصابون. في حالة ملامسة العين يجب غسلها بكثير من الماء وإستشارة طبيب فوراً. لا يجب التخلص من الكميات الزائدة بإلفائها في مجاري الماء. في جميع الأحوال يجب مراعاة القوانين البيئية والمهنية المحلية.

المعلومات المبينة في هذه المواصفة قائمة على إختبارات معملية و خبرات عملية. نظراً لإستخدام المنتج في ظروف خارجة عن تحكم الشركة فإننا لا نضمن إلا جودة المنتج نفسه. للشركة الحق في تغيير أي من البيانات بدون سابق إعلام.

للمزيد من المعلومات يرجى الإتصال بالإدارة الفنية



MAXIPLAST 3000

Product Description

MAXIPLAST 3000 is an economy water based mat paint based on Vinyl Copolymer for interior use as an undercoat for walls and ceilings.

Features:

- High hiding power for dry film
- High Workability
- High whiteness
- High Thinning capability

Technical Properties

Finish	Flat / Smooth	Drying Time @25°C	
Specific Gravity	1.66 ± 0.05	Touch Dry	1 Hours
Solids Volume	42% ± 2	Recoat	2 Hours
Thinner	Water	Complete	24 Hours
		Recommended DFT	50 microns

Processing Information

Substrate must be free of oil, algae, dirt and all other contaminants.
Product Should be well stirred before usage
Could be applied either by brush or roller.

Theoretical Coverage

4 - 5 Sqm/Kilogram/Coat (The Actual coverage depends on substrate nature and preparation, method of application, condition of tools, etc...)

Recommended Application System

- One coat PROTALL SEALER 121
- Two to three coats MAXIFLEX 700
- One Coat MAXIPLAST 3000 reduced 15% water.
- One coat MAXIPLAST 3000 reduced 10% water.

Storage

One year from date of production in original sealed package.
Product must be stored in well ventilated area away from direct sunlight, heat sources or freezing temperatures.

Health, Safety & Environment

Please observe the precautionary notice displayed on the container. Use under well ventilated conditions wearing suitable protective clothes. In case of breathing difficulties move to open air for minimum 10 minutes. In case of skin contact wash with water and soap. In case of eye contact, wash thoroughly with plenty of water and seek medical attention. Excess Paint should never be spilled in water sewers.
At all time local environmental laws and regulations should be maintained.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part. As application conditions are out of our control we can not guarantee but the quality of the product itself. PROTALL reserves the right to make any changes without prior notice.

For more Information please contact Technical Support

Headquarters: 27 Talaat Harb St. Alexandria
Tel.: +203 4868935/36 Fax.: +203 4868925

Factories & Technical Support: Km 25-26 Alex-Cairo road
Tel.: +203 4701110/20 Fax.: +203 4701141