

بروتال



مواصفة فنية متخصصة

51158.59-2018-V1

بروتاجوينت

الوصف والإستخدام

معجون أساس الأكرليك لملاً الفواصل و الشقوق و سد الفتحات الواسعة والضيقة وملاً الفوارغ التي قد تظهر عند اتصال الجدران و الارضيات أو بين الاسطح ذات الطبيعة المختلفة متوفر في نوعين:

بروتاجوينت ٥٨٠ لملئ الفتحات و الشقوق الرفيعة و الضيقة
بروتاجوينت ٥٩٠ لملئ الفتحات و الشقوق العميقة و الواسعة
متوفر باللون الابيض و يمكن تلويحه بألوان مختلفة حسب الرغبة

خصائص الدهان

المظهر النهائي	مطفئ	زمن الجفاف (٢٥°س)
الكثافة النوعية	١,٤٥ ± ٠,١	جفاف سطحي ١ ساعة
المواد الصلبة بالحجم	٦٩ ± ٣	جفاف لإعادة الطلاء ٢ ساعة
مادة التخفيف	—	جفاف نهائي ٢٤ ساعة
		سمك الفيلم الجاف المقترح ١٠٠ ميكرون (حسب طبيعة السطح)

تعليمات التطبيق

يجب أن يكون السطح خاليا تماما من الزيوت و الدهون و أي شوائب أخرى.
يطبق بروتاجوينت باستخدام سكين المعجون أو الفرشاه.

معدل التغطية

من ١ إلى ٢ متر مربع للكيلو للوجه الواحد (معدل الفرد يختلف باختلاف طبيعة السطح وطريقة تجهيزه والأدوات المستخدمة وفعاليتها).

نظام الدهان المقترح

تملاً الشقوق أو الفراغات أو الفتحات بأى من النوعين طبقاً للعمق و الاتساع و ينم ذلك دون أى تخفيف أو اضافات للمعجون.
يتم تطبيق المعجون على الاسطح المراد علاجها قبل دهان أى نوع من الدهانات أو المعاجين أو السيرلر.
يترك المعجون ليجف تماماً ثم يجهز السطح بعد ذلك كالمعتاد.

التخزين والصلاحيه

١٢ شهر في العبوة الأصلية المغلقة شرط سلامة العبوة وجودة التخزين.
يراعى التخزين في مكان جيد التهوية بعيداً عن أشعة الشمس المباشرة أو البرودة الشديدة.

الأمان والصحة والبيئة

يجب مراعاة التعليمات المدونة على العبوة. يراعى الإستخدام في مكان جيد التهوية وإرتداء الملابس الواقية المناسبة.
في حالة صعوبة التنفس يجب الخروج للهواء الطلق لمدة عشر دقائق على الأقل. في حالة ملامسة الجلد يجب إزالة المادة بالماء والصابون. في حالة ملامسة العين يجب غسلها بكثير من الماء وإستشارة طبيب فوراً.
لا يجب التخلص من الكميات الزائدة بإلقائها في مجاري الماء.
في جميع الأحوال يجب مراعاة القوانين البيئية والمهنية المحلية.

المعلومات المبينة في هذه المواصفة قائمة على إختبارات معملية وخبرات عملية. نظراً لإستخدام المنتج في ظروف خارجة عن تحكم الشركة فإننا لا نضمن إلا جودة المنتج نفسه. للشركة الحق في تغيير أي من البيانات بدون سابق إعلام.

للمزيد من المعلومات يرجى الإتصال بالإدارة الفنية

الإدارة العامة: ٢٧ طلعت حرب الإسكندرية

ت: ٣٦/٤٨٦٨٩٣٥ (٣) ف: ٤٨٦٨٩٢٥ (٣)

المصانع والإدارة الفنية: ك ٢٥ طريق إسكندرية القاهرة الصحراوي

ت: ٢/٤٧٠١١٠ (٣) ف: ٤٧٠١١٤١ (٣)

www.protall.com



Protall

Technical Data Sheet

51158.59-2018-V1

PROTAJOINT

Product Description

Special putty based on acrylic polymer to use on joints, cracks, holes, and the connections between horizontal and vertical surfaces.

PROTAJOINT is available in two types:

PROTAJOINT 580 for use to coat connections between horizontal and vertical surfaces, also to be used over very fine cracks to seal it and protect it.

PROTAJOINT 590 for use to fill wide cracks and holes.

Available in white as in an infinite number of colors upon request.

Technical Properties

Finish	Flat	Drying Time @25°C	
Specific Gravity	1.45 ± 0.1	Touch Dry	1 Hours
Solids Volume	69% ± 3	Recoat	2 Hours
Thinner		Complete	24 Hours
		Recommended DFT	40 microns

Processing Information

Substrate must be free of oil, algae, dirt and all other contaminants.
Could be applied either by brush or putty knife.

Theoretical Coverage

1 - 2 Sqm/Kilogram/Coat (The Actual coverage depends on substrate nature and preparation, method of application, condition of tools, etc...)

Recommended Application System

PROTAJOINT® is to be applied directly on fine cracks or between the horizontal and the vertical surfaces before applying any other coat.

Storage

One year from date of production in original sealed package.
Product must be stored in well ventilated area away from direct sunlight, heat sources or freezing temperatures.

Health, Safety & Environment

Please observe the precautionary notice displayed on the container. Use under well ventilated conditions wearing suitable protective clothes. In case of breathing difficulties move to open air for minimum 10 minutes. In case of skin contact wash with water and soap. In case of eye contact, wash thoroughly with plenty of water and seek medical attention.
Excess Paint should never be spilled in water sewers.
At all time local environmental laws and regulations should be maintained.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part. As application conditions are out of our control we can not guarantee but the quality of the product itself. PROTALL reserves the right to make any changes without prior notice.

For more Information please contact Technical Support

Headquarters: 27 Talaat Harb St. Alexandria
Tel.: +203 4868935/36 Fax.: +203 4868925

Factories & Technical Support: Km 25-26 Alex-Cairo road
Tel.: +203 4701110/20 Fax.: +203 4701141

www.protall.com